External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Die	Doped Silicon	Silicon (Si)	7440-21-3	0.06647	100.0	1
			Subtotal	0.06647	100	1
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.21373	100.0	3.21545
			Subtotal	0.21373	100	3.21545
Lead Frame	Copper alloy	Phosphorous (P)	7723-14-0	0.00928	0.03	0.13965
	Copper alloy	Iron (Fe)	7439-89-6	0.03404	0.11	0.51205
	Copper alloy	Copper (Cu)	7440-50-8	30.89852	99.86	464.8483
			Subtotal	30.94184	100	465.5
Post-plating	Pure metal	Tin (Sn)	7440-31-5	0.32238	100.0	4.85
			Subtotal	0.32238	100	4.85
Mould Compound	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	5.44789	8.0	81.96
	Filler	Silica fused	60676-86-0	55.15989	81.0	829.845
	Metal hydroxide	Metal hydroxide		0.47669	0.7	7.1715
	Carbon Black	Carbon black	1333-86-4	0.2043	0.3	3.0735
	Polymer	Epoxy resin system		6.80986	10.0	102.45
			Subtotal	68.09863	100	1024.5
Solder Wire	Tin alloy	Tin (Sn)	7440-31-5	0.03569	10.0	0.537
	Silver alloy	Silver (Ag)	7440-22-4	0.00714	2.0	0.1074
	Lead alloy	Lead (Pb)	7439-92-1	0.31411	88.0	4.7256
			Subtotal	0.35694	100	5.37
			Total	99.99999	100	1504.43545

## Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.